

## General Product Description

Strenx® 960 Plus is a structural steel that guarantees a minimum yield strength of 960 MPa.

Strenx® 960 Plus meets the requirements of EN 10 025-6 for the S960QL grade. Typical applications include demanding load-bearing structures.

Benefits include:

- Exceptional consistency within a sheet guaranteed by close tolerances
- High impact toughness which provides for good resistance to fractures
- Superior bendability and surface quality
- Weldability with excellent HAZ strength and toughness

## Dimension Range

Strenx® 960 Plus is available as cut to length sheets in thicknesses of 2.0 - 8.0 mm. Strenx 960 Plus is available in widths up to 1600 mm and lengths up to 16000 mm depending on thickness. Please contact your sales representative for more information regarding dimensions.

## Mechanical Properties

Thickness (mm)	Yield strength R <sub>eH</sub> <sup>1)</sup> (min MPa)	Tensile strength R <sub>m</sub> (MPa)	Elongation A <sub>5</sub> (min %)	Elongation A <sub>80</sub> (min%)	Min. inner bending radius for a 90° bend
2.0 - 2.9	960	980 - 1150	-	7	3.5 x t
3.0 - 8.0	960	980 - 1150	10	-	3.5 x t

The mechanical properties are tested in both longitudinal and transverse direction.

<sup>1)</sup> If ReH is not applicable then Rp0.2 is used.

## Impact Properties

Test direction	Min. Impact energy for Charpy V 10x10 mm test specimens
Longitudinal	30 J/ -40°C
Transverse	27 J/ -40°C

Impact testing according to EN ISO 148-1 is performed on thicknesses ≥ 6mm. For thicknesses between 6.0 - 8.0 mm, sub-size Charpy V-specimens are used. The specified min value is then proportional to the cross-sectional area of the specimen compared to a full-size specimen (10x10 mm).

## Chemical Composition (ladle analysis)

C (max %)	Si (max %)	Mn (max %)	P (max %)	S (max %)	Al <sub>tot</sub> (min %)
0.18	0.50	1.70	0.020	0.010	0.018

The steel is grain refined. \*)Intentional alloying elements.

## Carbon equivalent CET(CEV)

Thickness (mm)	2.0 - 8.0
Typical CET(CEV)	0.34 (0.50)

$$CET = C + \frac{Mn + Mo}{10} + \frac{Cr + Cu}{20} + \frac{Ni}{40}$$

$$CEV = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Cu + Ni}{15}$$

## Tolerances

More details are given in Strenx® Guarantees or on [www.ssab.com](http://www.ssab.com).

## Thickness

Tolerances according to Strenx® Thickness Guarantees. Strenx® Guarantees offer considerably narrower thickness tolerances compared to EN 10 051.

## Length and Width

Width and length tolerances according to SSAB standard. The SSAB standard offer narrower width and length tolerances compared to EN 10 051. Length tolerances only apply for cut to length sheets.

## Shape

Tolerances according to EN 10 051. Narrower tolerances according to the SSAB standard are available on request.

## Flatness

Tolerances according to Strenx® Flatness Guarantees Class A. Strenx® Flatness Guarantees offer narrower tolerances compared to EN 10 051. Flatness guarantees only apply for cut to length sheets.

## Surface Properties

According to EN 10 163-2 Class A, Subclass 3.

## Delivery Conditions

Strenx® 960 Plus is supplied in as rolled surface condition, pickled surface is available in a limited thickness range. The delivery condition is Q+T (Quenched and Tempered).

## Fabrication and Other Recommendations

### Welding, bending and machining

Strenx® 960 Plus has very good weldability with good toughness and strength in the welds. Strenx® 960 Plus has good forming and cutting performance.

Strenx® 960 Plus is not suited for applications requiring hot working or heat treatments at temperatures above 400°C, since the material then may lose its guaranteed properties.

For information concerning fabrication, see SSAB's brochures on [www.ssab.com](http://www.ssab.com) or consult Tech Support, [techsupport@ssab.com](mailto:techsupport@ssab.com).

Appropriate health and safety precautions must be taken when bending, welding, cutting, grinding or otherwise working on the product.

## Contact Information

[www.ssab.com/contact](http://www.ssab.com/contact)