

Strenx® Tube 700MH

General Product Description

Strenx® Tube 700MH is an HF-welded cold-formed structural hollow section made of hot-rolled high-strength steel with a minimum yield strength of 700 MPa.

Its high strength combined with naturally stiff form of welded hollow section enables construction of stronger and lighter structures. Strenx® Tube 700MH meets or exceeds the requirements of prEN 10219 (2016) and it is CE marked according to EN 1090-2. Typical applications include load-bearing structures in the lifting, handling and transportation segments.

Strenx® Tube 700MH is available in circular, square and rectangular shapes. Other shapes and sizes are available upon request.

The maximum length of the tubes is 12-18 meters, depending on the size. Longer or cut-to-length tubes are available upon request.

Hot dip galvanizing Strenx® Tube 700MH hollow sections may lead to cracking. Please consult SSAB Tech Support prior galvanization.

Dimension Range

Strenx® Tube 700MH is available at circular, square and rectangular shapes.

Circular	42.4 - 323.9 mm
Square	40x40 - 300x300 mm
Rectangular	50x30 - 400x200 mm
Wall thickness	2.0 - 10.0 mm
Mill length	6000 - 12 000/18 000 mm

Other shapes and sizes are available upon request.

Dimensions

Circular

Diameter	2.0mm (kg/m)	3.0mm (kg/m)	4.0mm (kg/m)	5.0mm (kg/m)	6.0mm (kg/m)	8.0mm (kg/m)	10.0mm (kg/m)
42.4 mm	1.99						
48.3 mm	2.28	3.35					
60.3 mm	2.88	4.24					
76.1 mm	3.65	5.41	7.11				
88.9 mm		6.36	8.38	10.4			
101.6 mm		7.29	9.63	11.9			
108 mm		7.77	10.3	12.7			
114.3 mm		8.23	10.9	13.5			
127 mm		9.17	12.1	15.0			
133 mm		9.62	12.7	15.8			
139.7 mm		10.1	13.4	16.6	19.8	26.0	32.0
168.3 mm			16.2	20.1	24.0	31.6	39.0
193.7 mm				23.3	27.8	36.6	45.3
219.1 mm				26.4	31.5	41.7	51.6
244.5 mm				29.5	35.3	46.7	57.8
273 mm				33.1	39.5	52.3	64.9
323.9 mm					47.0	62.3	77.4

Recommended minimum batch sizes on mill orders.

Minimum batch size, m	Metric weight, kg/m
3000 ≤ 5
1500	< 5..... ≤ 20
500	> 20.....

Square

Height x Width	2.0mm (kg/m)	3.0mm (kg/m)	4.0mm (kg/m)	5.0mm (kg/m)	6.0mm (kg/m)	8.0mm (kg/m)	10.0mm (kg/m)
40 x 40 mm	2.31	3.30					
50 x 50 mm	2.93	4.25					
60 x 60 mm	3.56	5.19	6.71				
70 x 70 mm		6.13	7.97	9.70			
80 x 80 mm		7.07	9.22	11.3			
90 x 90 mm			10.5	12.8			
100 x 100 mm			11.7	14.4	17.0	21.4	
120 x 120 mm			14.3	17.6	20.8	26.4	
140 x 140 mm			16.8	20.7	24.5	31.4	38.1
150 x 150 mm			18.0	22.3	26.4	34.0	41.3
160 x 160 mm				23.8	28.3	36.5	44.4
180 x 180 mm				27.0	32.1	41.5	50.7
200 x 200 mm					35.8	46.5	57.0
220 x 220 mm					39.6	51.5	63.2
250 x 250 mm					45.2	59.1	72.7
300 x 300 mm						71.6	88.4

Recommended minimum batch sizes on mill orders.

Minimum batch size, m	Metric weight, kg/m
3000 ≤ 5
1500	< 5..... ≤ 20
500	> 20.....

Rectangular

Height x Width	2.0mm (kg/m)	3.0mm (kg/m)	4.0mm (kg/m)	5.0mm (kg/m)	6.0mm (kg/m)	8.0mm (kg/m)	10.0mm (kg/m)
50 x 30 mm	2.31						
60 x 40 mm	2.93	4.25					
70 x 50 mm	3.56	5.19	6.71				
80 x 40 mm	3.56	5.19	6.71				
80 x 60 mm		6.13	7.97				
90 x 50 mm		6.13	7.97				
100 x 50 mm		6.60	8.59				
100 x 60 mm		7.07	9.22				
100 x 80 mm			10.5				
120 x 60 mm			10.5	12.8			
120 x 80 mm			11.7	14.4	17.0	19.4	
150 x 100 mm			14.9	18.3	21.7	27.7	
160 x 80 mm			14.3	17.6	20.8	26.4	
180 x 100 mm			16.8	20.7	24.5	31.4	38.1
200 x 100 mm			18.0	22.3	26.4	34.0	41.3
200 x 120 mm				23.8	28.3	36.5	44.4
250 x 100 mm					31.11	40.23	49.11
250 x 150 mm					35.8	46.5	57.0
260 x 180 mm					39.6	51.5	63.2
300 x 200 mm					45.2	59.1	72.7
400 x 200 mm						71.6	88.4

Recommended minimum batch sizes on mill orders.

Minimum batch size, m 3000 1500 500	Metric weight, kg/m ≤ 5 < 5..... ≤ 20 > 20.....
--	--

Mechanical Properties

Yield strength R _{p0.2} (min MPa)	Tensile Strength R _m (MPa)	Elongation A ₅ ²⁾ (min %)	Charpy-V -20°C 10x10 mm test specimen ¹⁾ (min J)
700	750 - 950	10	40

Mechanical properties meet the requirements of prEN 10219 (2016).

The mechanical properties for rectangular hollow sections are tested by SSAB on the longer side of the cross section.

¹⁾ Impact testing according to EN ISO 148-1 is performed on thicknesses ≥ 6mm. The specified minimum value corresponds to a full-size specimen.

²⁾ The hollow sections with D/T < 15 (round) or (B + H)/2T < 12,5 (rectangular and square), the minimum value of elongation is reduced by 2.

Chemical Composition (ladle analysis)

C (max %)	Si (max %)	Mn (max %)	P (max %)	S (max %)	Al _{tot} (min %)	Nb (max %)	V (max %)	Ti (max %)
0.12	0.25	2.10	0.020	0.012	0.015	0.090 ¹⁾	0.20 ¹⁾	0.15 ¹⁾

Chemical composition meets or **exceeds** the requirements of prEN 10219 (2016).

In addition, boron (B), molybdenum (Mo), nickel (Ni) or copper (Cu) may be used as alloying elements either singly or in combination.

The steel is grain refined.

1) Sum of Nb, V and Ti = max 0.22%

Carbon equivalent

Typical CET	0.24
Typical CEV	0.38

$$CET = C + \frac{Mn + Mo}{10} + \frac{Cr + Cu}{20} + \frac{Ni}{40}$$

$$CEV = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Cu + Ni}{15}$$

Tolerances

Characteristic	Circular hollow sections Tolerances meet or exceed the requirements of EN 10219
Outside diameter (D) ¹⁾	±1%, however a minimum of ±0.5 mm and a maximum of ±10 mm
Out-of-roundness	2%, when D/T ≤ 100
Thickness (T)	When D ≤ 323.9 mm: -5%/+10%, with a minimum of ±0.2 mm and maximum ±0.5 mm When 355.6 ≤ D ≤ 406.4 mm ³⁾ : ±10%, when T ≤ 5 mm / ±0.5 mm, when T > 5 mm When D > 406.4 mm ³⁾ : ±10%, with a maximum of ±2 mm
Straightness	0.20% of total length and 3 mm over any 1 m length
Mass per unit length	Individual tube: ±6%
Mill length	0/+50 mm, 6000 ≤ L ≤ 12000 - 18000 mm (standard lengths 6000 & 12000 mm)
Exact length	Agreed at the time of enquiry and order

¹⁾ All external dimensions are measured with a minimum distance from the end of the section. The distance must be a minimum of 100 mm.

Characteristic	Square hollow sections Tolerances meet or exceed the requirements of EN 10219
Outside dimensions (B, H) ¹⁾	When B, H < 100 mm ± 1 % minimum ± 0.5 mm When 100 mm \leq B, H \leq 200 mm: ± 0.8 % When B, H > 200 mm: ± 0.6 %
Thickness (T)	-5%/ +10 %, with a minimum of ± 0.2 mm and maximum ± 0.5 mm
External corner profile	When T \leq 6 mm: 1.6 x T-2.4 x T When 6 mm < T \leq 10 mm: 2.0 x T-3.0 x T When T > 10 mm: 2.4 x T-3.6 x T
Squareness of side	90° ± 1 °
Concavity/convexity	0.8%, with a minimum of 0.5 mm
Twist	2 mm + 0.5 mm/m
Straightness	0.15% of total length and 3 mm over any 1 m length
Mass per unit length	Individual tube: ± 6 %
Mill length	0/+50 mm, 6000 \leq L \leq 12000 - 18000 mm (standard lengths 6000 & 12000 mm)
Exact length	Agreed at the time of enquiry and order

¹⁾ All external dimensions are measured with a minimum distance from the end of the section. The distance must be a minimum of 100 mm.

Characteristic	Rectangular hollow sections Tolerances meet or exceed the requirements of EN 10219
Outside dimensions (B, H) ¹⁾	When B, H < 100 mm ± 1 % minimum ± 0.5 mm When 100 mm \leq B, H \leq 200 mm: ± 0.8 % When B, H > 200 mm: ± 0.6 %
Thickness (T)	-5%/ +10 %, with a minimum of ± 0.2 mm and maximum ± 0.5 mm
External corner profile	When T \leq 6 mm: 1.6 x T-2.4 x T When 6 mm < T \leq 10 mm: 2.0 x T-3.0 x T When T > 10 mm: 2.4 x T-3.6 x T
Squareness of side	90° ± 1 °
Concavity/convexity	0.8%, with a minimum of 0.5 mm
Twist	2 mm + 0.5 mm/m
Straightness	0.15% of total length and 3 mm over any 1 m length
Mass per unit length	Individual tube: ± 6 %
Mill length	0/+50 mm, 6000 \leq L \leq 12000 - 18000 mm (standard lengths 6000 & 12000 mm)
Exact length	Agreed at the time of enquiry and order

¹⁾ All external dimensions are measured with a minimum distance from the end of the section. The distance must be a minimum of 100 mm.

Delivery Conditions

The tubes are cold formed and high frequency welded from thermomechanically rolled steel.

Fabrication and Other Recommendations

Welding, bending and machining

Strenx® Tube 700 MH has good weldability, including corner region, and it is suitable for thermal cutting. All the common welding methods are suitable with matching or undermatching consumables.

Tubes can also be sawed and machined with regular tools. Bending of the tubes is also possible, typically at least 5xD (five times the diameter) bending radius can be achieved with regular draw bending tooling.

Hot dip galvanizing Strenx® Tube 700 MH hollow sections may lead to cracking. Please consult Tech Support prior galvanization.

For information concerning fabrication, see SSAB's brochures on www.ssab.com or consult Tech Support, techsupport@ssab.com.

Appropriate health and safety precautions must be taken when bending, welding, cutting, grinding or otherwise working on the product.

Contact Information

www.ssab.com/contact